

File :Q:\GCMS-08 Minimal\DATA\20210818\03- KM.D
Operator : Organic QC Lab
Acquired : 18 Aug 2021 11:01 using AcqMethod Hy_PAH_15cm_S10.M
Instrument : GCMS 8
Sample Name: PLAS-PL-007S
Misc Info : Polycizer Butyl Oleate in Hexane
Vial Number: 44



Column: DB-5MS UI, 30m x 0.25mm ID x 0.25µm
Oven Program: 80°C, 17°C/min to 340°C (hold 8min)
GC Parameters: Pulsed split 40psi 0.5min, 10psi constant flow
Split 20:1, 1µl inj.; GC/MS; Injector 270°C

